

Petroleum Jelly

Snow White

Date: 2011-03-04

Typical Specifications

Property	Unit	Test Method	Results	
Code No.	—	—	00900	00905
Color	—	IP-17 cell 2"	0 – 1.3y	0.7 Y
Congealing	°C	ASTM D-938	50 -60	50 -60
Penetration @ 25 °C	—	ASTM D-937	100 - 120	140 – 160
Viscosity @100 °C	c.St	ASTM D-445	5.5 – 7	5 – 6.5
SP Gravity	gr/cm ³	ASTM D-1298	0.78 -0.89	0. 815 – 0. 880
Flash Point	°C	ASTM D-92	Min 190	Min 212
Polycyclic Aromatic Hydrocarbons	—	B.P 2007	Passed	Passed
Acidity or Alkalinity	—	B.P 2007	Passed	Passed
Light Absorption	—	B.P 2007	Max 0.5	—
Sulphated Ash	—	B.P 2010	—	Max 0.05
Drop Melting Point	°C	ASTM D-87	55 - 70	52 – 55
Odour	—	—	Odour less	Odour less

Please refer to the Material Safety Data Sheet (M.S.D.S) for additional information.